



5100, 5200 StuccoCure

Epoxy Acrylic Hybrid
Stucco Primer

Product Description

StuccoCure from SRK Coatings, a semi-transparent deep penetrating primer for stucco, hydrates, hardens, seals, and cures new unpainted stucco. In just 24 hours, the cured stucco is ready for the finish coat of paint! StuccoCure penetrates the stucco delivering a permanent, breathable water repellency into the clean stucco. The resulting surface retains a stable pH which helps to control unsightly efflorescence deposits and rapid color burnout associated with hot stucco. Additionally, StuccoCure hardens the stucco so that hairline cracks are minimized or eliminated altogether. The result is a long lasting, brand-new look for the owner and for the builder.

Performance Features

- Rapid curing of stucco
- Paint in just 24 hours
- Control efflorescence, color burnout, cracks
- Water repellent

Product Specifications

Resin Type:	Epoxy Acrylic Hybrid
Color Range	Tracer Yellow - 5100 Clear - 5200
Finish:	Flat
Drying Time:	To touch: 30-60 minutes For topcoat: 2 hours or more
Practical Coverage:	150 sf/gal on coarse stucco 250 sf/gal on smooth stucco
Weight per gallon:	8.58 lbs.
Shelf Life	2 years (unopened container) <90°
Size:	5 Gallon, Drum, Tote
VOC:	<.41 lbs/gal and <49.25 grams/liter
Cleanup:	Water
Solids by weight:	15.22%
Solids by volume:	13.00%

Surface Preparation

StuccoCure should be applied to raw stucco anytime between eight hours and 72 hours after the final coat of stucco is applied. The surface of raw stucco must be clean, free from all dirt, dust, grease, and wax, and damp. Spray raw stucco with water from a garden hose, and begin to dry to a damp surface (approximately 15-30 minutes) before applying StuccoCure.

Application

StuccoCure MUST be stirred/shaken thoroughly prior to use, occasionally during use, and after any delays in application. Protect all non-stucco surfaces (glass, frames, aluminum, concrete, brick, wood, etc.) prior to spraying. Failure to protect these areas may result in staining.

StuccoCure should be applied with airless spray equipment set at the lowest pressure possible, using a 517 or 519 tip. Make sure all areas are covered with a generous application. However, do not apply more than one coat of StuccoCure. Applying a second coat may result in the formation of surface participates, and require sand blasting or wire brushing.

Top Coat

Top coats can be applied to the surface within 24-36 hours after applying StuccoCure. We suggest that you backroll the top coat with a water repellent 100% acrylic paint.

Thinning

No thinning is required, and it is not recommended.

CAUTIONS

Do not apply when temperature is below 50 degrees F. Do not apply to any exterior surface when rain is expected within 24 hours. Keep from freezing. Keep all unused material in tightly closed containers. Keep away from children. Do not take internally.

WARNING: If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.



Phoenix, AZ 85076

www.srkcoatings.com

LIMITATION OF LIABILITY To the best of our knowledge, the technical data contained herein are true and accurate at the date of issuance but are subject to change without prior notice. We guarantee our product to conform to the specifications contained herein. WE MAKE NO OTHER WARRANTY OR GUARANTEE OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSE. Liability, if any, is limited to replacement of the product or refund of the purchase price. LABOR OR COST OF LABOR AND OTHER CONSEQUENTIAL DAMAGES ARE HEREBY EXCLUDED.